

Classic 50

SKC Window Film

Advantage -

1. Drive cooler by reducing excessive solar heat
2. Better eye comfort
3. Great maintenance with less scratch
4. Long life indoor fabric from fading

Clear Hard-Coating

Optical Grade PET Film (23±1μm)

Adhesive

Sputter Film (23±1μm)

UV-Cut PSA

Silicone Release Film(23μm)

Visible Light Transmitted		58.2%	KS L 2016 ISO 9050
Visible Light Reflected	External	9.1%	KS L 2016 ISO 9050
	Internal	11.4%	
Solar Heat	Reflected	8.2%	ISO 9050
	Absorbed	38.6%	
	Transmitted	53.2%	
IR Rejected		47%	ISO 9050
UV Rejected		99%	KS L 2016 ISO 9050
Total Solar Energy Rejected (TSER)		37.8%	ISO 9050

Thickness	2Mil/2Ply	
Shading Coefficient	0.64	JIS A 5759
Solar Heat Gain Coefficient (SHGC)	0.56	KS L 2514
Scratch Resistant	>2H	ASTM D3363
Adhesion of Hard-Coated Surface	5B (0% peel-off)	ASTM D3359